

QUICKBUND

CHEMICAL RESISTANCE

GUIDE

EXPOSURE RATING

AFFF	A
Acetic Acid (5%)	B
Acetic Acid (50%)	C
Ammonium Phosphate	T
Ammonium Sulphate	T
Antifreeze (ethylene glycol)	A
Animal oil	A
Aqua Regie	X
ASTM Fuel (100% Iso-octane)	A
ASTM Oil #2 (Flash point 240°C)	A
ASTM Oil #3	A
Benzene	X
Calcium Chloride Solution	T
Calcium Hydroxide	T
20% Chlorine Solution	A
Clorox	A
Corn Oil	A
Crude Oil	A
Diesel Fuel	A
Ethanol	A
Ethyl Acetate	C
Ethyl Alcohol	A
Fertilizer Solution	A
#2 Fuel Oil	A
#6 Fuel Oil	A
Furfural	X
Gasoline	B
Glycerin	A
Hydraulic Fluid - Petroleum Based	A
Hydraulic Fluid - Phosphate Ester Based	C
Hydrocarbon Type II (40% aromatic)	C
Hydrochloric Acid (50%)	A
Hydrofluoric Acid (5%)	A
Hydrofluoric Acid (50%)	A
Hydrofluosilicic Acid (30%)	A
Isopropyl Alcohol	T
Ivory Soap	A
Jet A	A
JP-4 Jet Fuel	A
JP-4 Jet Fuel	A
JP-5 Jet Fuel	A
JP-8 Jet Fuel	A
Kerosene	A
Magnesium Chloride	T
Magnesium Hydroxide	T
Methanol	A
Methyl Alcohol	A

EXPOSURE RATING

Methyl Ethyl Ketone	X
Mineral Spirits	A
Naptha	A
Nitric Acid (5%)	B
Nitric Acid (50%)	C
Perchloroethylene	C
Phenol	X
Phenol Formaldehyde	B
Phosphoric Acid (50%)	A
Phosphoric Acid (100%)	C
Phthalate Plasticizer	C
Potassium Chloride	T
Potassium Phosphate	T
Raw Linseed Oil	A
SAE-30 Oil	A
Salt Water (25%)	B
Sea Water	A
Sodium Acetate Solutions	T
Sodium Bisulfite Solution	T
Sodium Hydroxide (60%)	A
Sodium Phosphate	T
Sulfuric Acid (50%)	A
Tanic Acid (50%)	A
Toluene	C
Transformer Oil	A
Turpentine	A
Urea Formaldehyde	A
UAN	A
Vegetable Oil	A
Water (93.3°C)	A
Xylene	X
Zinc Chloride	T

RATING KEY:

- A - Fluid has little or no effect
- B - Fluid has minor to moderate effect
- C - Fluid has severe effect
- T - No data - likely to be acceptable
- X - No data - not likely to be acceptable